

List of UL-Styles (Multicore cables)

UL-Style No.	Insulation Material	Voltage Volt	Temp. °C	Insulation thickness mm	AWG Size	UL-Style No.	Insulation Material	Voltage Volt	Temp. °C	Insulation thickness mm	AWG Size
2006	PVC	300	80	1,14	20-16	2464	variable	300	80	-	30
2007	PVC	300	90	1,14	20-16	2468	PVC	300	80	0,38	32-16
2012	PVC	300	80	1,52	18-16	2474	PVC	600	105	-	26-14
2015	PVC	300	80	1,52	18-16	2477	PVC	600	60	-	33-16
2030	PVC	600	80	1,91	14-10	2483	PVC	600	105	-	26-16
2031	PVC	600	90	1,91	14-10	2489	PVC	600	60	-	18
2032	PVC	600	105	1,91	14-10	2490	AWM	not specified*	60	AWM	min. 36
2089	PVC	300	60	-	20-18	2493	PP	600	60	-	30-16
2090	PVC	300	60	-	20-18	2498	PE	300	80	-	28-16
2091	PVC	300	60	-	20-18	2501	PVC	600	105	-	30
2092	PE	300	60	-	26-16	2502	variable	30	80	-	-
2093	PE	300	60	-	26-16	2504	PVC	600	105	-	20-14
2094	PE	300	60	-	26-16	2507	PVC	600	60	-	26-16
2095	PVC	300	90	-	32-16	2516	PVC	600	105	-	30-9
2096	PVC	300	80	-	30-16	2517	PVC	300	105	-	32-16
2097	PVC	300	80	-	30-18	2532	PVC	30	60	-	30-16
2098	PVC	300	90	-	26-16	2535	PVC	30	80	-	30-16
2099	PVC	300	90	-	26-16	2548	PE	300	80	-	-
2100	PVC	300	90	-	26-16	2549	PVC	300	90	-	30-16
2101	PVC	300	105	0,38	30-16	2550	AWM	600	90	AWM	min. 40
2102	PVC	300	105	-	30-16	2551	AWM	30	105	AWM	min. 40
2103	PVC	300	105	0,38	30-16	2560	PVC	30	60	-	30
2106	PE	600	60	-	26-12	2564	PVC	125	75	-	22
2107	PE	600	60	-	26-12	2567	PVC	600	60	-	-
2108	PE	600	60	-	26-12	2570	PVC	600	80	-	30-9
2112	PVC	300	80	0,38	26-16	2571	PVC	-	80	-	30-16
2113	PVC	300	80	0,38	26-16	2574	AWM	30	105	AWM	min. 40
2114	PVC	300	80	0,38	26-16	2576	PVC	150	80	-	30-9
2115	PVC	600	80	-	26-16	2582	PE	150	60	-	30-16
2116	PVC	600	80	-	26-16	2584	PVC	125	80	-	30-9
2117	PVC	600	80	-	26-16	2586	PVC	600	105	-	30-9
2121	PVC	300/600	90	0,38	26-16	2587	PVC	600	90	-	30-9
2122	PVC	300/600	90	0,38	26-16	2589	AWM	30	105	AWM	see AWM requirements
2123	PVC	300/600	90	0,38	26-16	2598	VAR	300	60	-	30-16
2124	PVC	600	90	0,76	28-9	2606	PE	300	60	-	30
2125	PVC	600	90	0,76	28-9	2610	labeled Style 1007	300	80	labeled Style 1007	see 1007 requirements
2126	PVC	600	90	0,76	28-9	2614	AWM	30	105	AWM	min. 40
2127	PVC	600	105	0,76	28-9	2623	PE	30	80	-	30-20
2128	PVC	600	105	0,76	28-9	2626	AWM	30	80	AWM	not specified*
2129	PVC	600	105	0,76	28-9	2629	PE	300	80	-	30-16
2243	PVC	300	105	1,14	20-16	2630	AWM	125	90	AWM	30-9
2261	PVC	300	105	0,76	18	2631	AWM	not specified*	90	AWM	min. 40
2262	PE	600 (isol.)	60	0,76	26-16	2637	AWM	30	90	AWM	min. 40
		300 (Jacket)				2653	AWM	600	90	AWM	36-6
2263	PE	600 (isol.)	60	0,76	26-16	2654	AWM	300	90	AWM	36-6
		300 (Jacket)				2655	PVC	300	80	-	33-10
2264	PE	600 (isol.)	60	0,76	26-16	2656	AWM	600	80	AWM	36-6
		300 (Jacket)				2660	AWM	not specified*	60	AWM	-
2265	PVC	300	80	0,38	26-16	2661	AWM	300	105	AWM	36-6
2266	PVC	300	80	-	26-16	2662	PVC	600	105	-	33-10
2267	PVC	300	80	-	36-30	2668	AWM	30	60	AWM	min. 40
2268	PVC	300	80	-	26-16	2678	PVC	30	105	-	-
2269	PVC	300	80	-	26-16	2704	PVC	30	60	-	30
2270	PVC	300	80	-	26-16	2778	AWM	150	60	AWM	30-16
2271	as for SVT	300	60	wie für SVT	26-16	2789	AWM	30	60	AWM	see AWM
2272	as for SVT	300	60	as for SVT	26-16	2833	AWM	30	60	AWM	-
2273	as for SVT	300	60	as for SVT	26-16	2835	PP	30	80	-	22
2274	as for SVT	300	60	as for SVT	26-16	2919	PP	30	80	-	28-18
2275	as for SVT	300	60	as for SVT	26-16	2920	AWM	30	60	AWM	min. 40
2276	as for SVT	300	60	as for SVT	26-16	2921	AWM	30	60	AWM	min. 40
2277	as for SVT	300	60	as for SVT	26-16	2930	AWM	not specified*	105	AWM	min. 40
2278	as for SVT	300	60	as for SVT	26-16	2931	AWM	125	105	AWM	min. 40
2279	as for SVT	300	60	as for SVT	26-16	2937	AWM	300	80	AWM	AWM
2280	as for SVT	300	60	as for SVT	26-16	3071	S/GB	600	200	0,76	18-14
2317	PE	600	60	-	26-16	3075	S/GB	600	200	0,76	10-2
2351	PE	600	80	-	26-16	3173	XLPE	600	125	0,76	26-9
2352	PE	300	80	-	26-16	3199	XLPE	300	105	0,38	22-16
2353	PE	300	80	-	26-16	3212	SIR	600	150	1,14	26-10
2354	PE	600	80	-	26-16	3213	SIR	600	150	1,52	8-2
2355	PE	600	80	-	26-16	3214	SIR	600	150	1,91	1-4/0
2376	PVC	300	105	-	-	3239	SIR	VAR	150	VAR	24-10
2384	variable	30	60	-	30	3265	XLPE	150	125	0,25	28-20
2385	VAR	30	60	-	30	3266	XLPE	300	125	0,38	26-16
2386	VAR	30	60	-	30	3271	XLPE	600	125	VAR	24-12
2387	VAR	30	60	-	30	3272	XLPE	600	125	VAR	22-4
2388	PVC	30	60	-	-	3291	XPVC	300	105	-	26-16
2405	PVC	300	80	-	30-16	20063	PE	300	80	0,5	28-16
2439	PE	600	80	-	26-16	20083	AWM	300	80	AWM	diverse AWM
2448	variable	30	60	-	30	20601	AWM	300	80	AWM	AWM
2461	PVC	300	80	-	26-16						
2462	PVC	300	60	-	-						
2463	PVC	600	80	-	26-10						

* not specified

